

**Polimaxx 2500H**

PP

IRPC

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	25	MPa	ASTM D 638
Elongation at Yield	22	%	ASTM D 638
Rockwell Hardness	R 87	-	ASTM D 785
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	92	°C	ASTM D 648
<b>Processing Recommendation Extrusion</b>			
Melt temperature	190 - 240	°C	-

**Characteristics****Processing**

Other Extrusion, Blow Molding

**Special Characteristics**

High impact or impact modified

**Features**

Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR, RoHS compliant

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

Europe, Asia Pacific