

Polimaxx 3325M

PP

IRPC

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	9	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26	MPa	ASTM D 638
Elongation at Yield	37	%	ASTM D 638
Rockwell Hardness	R 88	-	ASTM D 785

Other Standards ^[5]	Value	Unit	Test Standard
Charpy notched impact strength, +23°C	4.5	kJ/m ²	DIN 53453

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	75	°C	ASTM D 648

Processing Recommendation Extrusion	Value	Unit	Test Standard
Type of extrusion	film	-	-
Melt temperature	200 - 240	°C	-

Characteristics

Processing

Film Extrusion

Applications

Packaging

Features

Copolymer, Random Copolymer

Regional Availability

Europe, Asia Pacific

Certifications

Food contact, Food approval FDA 21 CFR, RoHS compliant