

POLYCOMP PDR CB 08

PP

PolyPacific Pty Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	32	MPa	ASTM D 638
Elongation at Break	150	%	ASTM D 638
Flexural Modulus	1610	MPa	ASTM D 790
Rockwell Hardness	R 104	-	ASTM D 785
Shore D Hardness	68	-	ASTM D 2240
Izod Impact notched, 1/8 in	76	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1170	J/m	ASTM D 256
Thermal properties			
ASTM Data			
Coefficient of Thermal Expansion, MD	100	E-6/K	ASTM D 696
DTUL @ 66 psi	127	°C	ASTM D 648
Other properties			
Density	910	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Features

High Crystallinity, Copolymer

Delivery form

Granules

Regional Availability

Asia Pacific

Special Characteristics

High impact or impact modified