

POLYfill PPC 200 E20

PP

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	32	MPa	ISO 527
Yield strain	17	%	ISO 527
Flexural modulus, 23°C	1200	MPa	ISO 178
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific

Delivery form

Granules