

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	2	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1600	MPa	ISO 527
^[C] Yield stress	15	MPa	ISO 527
^[C] Yield strain	3.7	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	35	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	3	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	94	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	57	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1060	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Other Extrusion

Special Characteristics

Flame retardant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa