

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	10	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1400	MPa	ISO 527
^[C] Yield stress	28	MPa	ISO 527
^[C] Yield strain	10	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	19	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	2.3	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	120	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	94	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
^[C] Oxygen index	27	%	ISO 4589-1/-2

ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.5	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	940	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Injection Molding, Profile Extrusion, Thermoforming

Delivery form
Granules

Additives
Release agent

Special Characteristics
Flame retardant

Features
Copolymer, Homopolymer

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa