

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	27	MPa	ASTM D 638
Elongation at Break	400	%	ASTM D 638
Flexural Modulus	1000	MPa	ASTM D 790
Izod Impact notched, 1/8 in	76.9	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	3.05	mm	-
DTUL @ 66 psi	85	°C	ASTM D 648
DTUL @ 264 psi	50	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	950	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Features

Copolymer

#### Regional Availability

North America