

**POLYFLAM® RPP 1729**

PP

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>30</b>	MPa	ASTM D 638
Elongation at Break	<b>200</b>	%	ASTM D 638
Flexural Modulus	<b>1400</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>30.7</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>3</b>	mm	-
DTUL @ 66 psi	<b>85</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>55</b>	°C	ASTM D 648

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>18.1</b>	kV/mm	ASTM D 149

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1000</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

Flame retardant

**Regional Availability**

North America

**Features**

Homopolymer