

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	19	MPa	ASTM D 638
Elongation at Break	20	%	ASTM D 638
Flexural Modulus	758	MPa	ASTM D 790
Rockwell Hardness	R65	-	ASTM D 785
Izod Impact notched, 1/8 in	649	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	82	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Features

Copolymer, Impact Copolymer

#### Special Characteristics

High impact or impact modified

#### Regional Availability

North America