

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|-------------------|---------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.005 | mm/mm | ASTM D 955 |
| Mechanical properties | | | |
| ASTM Data | | | |
| Tensile Strength at Yield | 70 | MPa | ASTM D 638 |
| Elongation at Break | 5 | % | ASTM D 638 |
| Flexural Modulus | 4231 | MPa | ASTM D 790 |
| Flexural Strength | 110 | MPa | ASTM D 790 |
| Rockwell Hardness | R107 | - | ASTM D 785 |
| Izod Impact notched, 1/8 in | 66.3 | J/m | ASTM D 256 |
| Thermal properties | | | |
| ASTM Data | | | |
| DTUL @ 66 psi | 159 | °C | ASTM D 648 |
| DTUL @ 264 psi | 111 | °C | ASTM D 648 |
| Other properties | | | |
| Density | 1040 | kg/m ³ | ASTM D 792 |

Characteristics

Delivery form

Black

Regional Availability

North America

Features

Chemically Coupled Reinforcement