

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	21	MPa	ASTM D 638
Flexural Modulus	2098	MPa	ASTM D 790
Flexural Strength	33	MPa	ASTM D 790
Izod Impact notched, 1/8 in	61.5	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	114	°C	ASTM D 648
DTUL @ 264 psi	71	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Black

Regional Availability

North America