

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	22	MPa	ASTM D 638
Flexural Modulus	2000	MPa	ASTM D 790
Izod Impact notched, 1/8 in	46.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	105	°C	ASTM D 648
DTUL @ 264 psi	58	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America