

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	23	MPa	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	1655	MPa	ASTM D 790
Rockwell Hardness	R86	-	ASTM D 785
Izod Impact notched, 1/8 in	103	J/m	ASTM D 256
Thermal properties			
Value	Unit	Test Standard	
ASTM Data			
DTUL @ 66 psi	102	°C	ASTM D 648
Other properties			
Value	Unit	Test Standard	
Density	1000	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Applications

Automotive

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

North America