

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26.2	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	2841	MPa	ASTM D 790
Rockwell Hardness	R88	-	ASTM D 785
Izod Impact notched, 1/8 in	14.9	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	115	°C	ASTM D 648
DTUL @ 264 psi	80	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Features

Homopolymer

Delivery form

Black

Regional Availability

North America