

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	25	MPa	ASTM D 638
Flexural Modulus	2890	MPa	ASTM D 790
Rockwell Hardness	R69	-	ASTM D 785
Izod Impact notched, 1/8 in	255	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	117	°C	ASTM D 648
DTUL @ 264 psi	64	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1150	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Regional Availability

North America