

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	24	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 638
Flexural Modulus	1940	MPa	ASTM D 790
Rockwell Hardness	R73	-	ASTM D 785
Izod Impact notched, 1/8 in	76.9	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	118	°C	ASTM D 648
DTUL @ 264 psi	60	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

North America

Features

Homopolymer