

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Elongation at Break	20	%	ASTM D 638
Flexural Strength	24.1	MPa	ASTM D 790
Izod Impact notched, 1/8 in	267	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	105	°C	ASTM D 648
DTUL @ 264 psi	51.1	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Features

Chemically Coupled Reinforcement

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America