

POLYFORT® PP 1329

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26	MPa	ASTM D 638
Flexural Modulus	825	MPa	ASTM D 790
Izod Impact notched, 1/8 in	2.21	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	82	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics**Features**

Copolymer, Impact Copolymer

Regional Availability

North America

Applications

Automotive