

POLYFORT® PP 1329HU

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25	MPa	ASTM D 638
Elongation at Break	125	%	ASTM D 638
Flexural Modulus	800	MPa	ASTM D 790
Rockwell Hardness	R83	-	ASTM D 785
Izod Impact notched, 1/8 in	106	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	80	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	903	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

U.V. stabilized or stable to weather

Regional Availability

North America

Features

Copolymer, Impact Copolymer