

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	21.4	MPa	ASTM D 638
Elongation at Break	10	%	ASTM D 638
Flexural Modulus	897	MPa	ASTM D 790
Rockwell Hardness	R70	-	ASTM D 785
Izod Impact notched, 1/8 in	108	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	84	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

U.V. stabilized or stable to weather

Features

Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America