

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	21.4	MPa	ASTM D 638
Elongation at Break	80	%	ASTM D 638
Flexural Modulus	896.3	MPa	ASTM D 790
Rockwell Hardness	R70	-	ASTM D 785
Izod Impact notched, 1/8 in	171	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	62.8	°C	ASTM D 648
DTUL @ 264 psi	43.3	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America