

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	21	MPa	ASTM D 638
Elongation at Yield	15	%	ASTM D 638
Elongation at Break	250	%	ASTM D 638
Flexural Modulus	910.1	MPa	ASTM D 790
Rockwell Hardness	R85	-	ASTM D 785
Izod Impact notched, 1/8 in	133	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	85	°C	ASTM D 648
DTUL @ 264 psi	50	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Regional Availability

North America

#### Features

Copolymer