

POLYFORT® PP 1930UX

PP

LyondellBasell Industries

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength at Yield | 23 | MPa | ASTM D 638 |
| Flexural Modulus | 930.8 | MPa | ASTM D 790 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| DTUL @ 66 psi | 90 | °C | ASTM D 648 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 904 | kg/m ³ | ASTM D 792 |

Characteristics**Special Characteristics**

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

North America

Features

Copolymer