

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	30	MPa	ASTM D 638
Elongation at Yield	20	%	ASTM D 638
Flexural Modulus	1275	MPa	ASTM D 790
Rockwell Hardness	R88	-	ASTM D 785
Izod Impact notched, 1/8 in	64.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	100	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

North America