

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	24	MPa	ASTM D 638
Elongation at Break	20	%	ASTM D 638
Flexural Modulus	950	MPa	ASTM D 790
Flexural Strength	30	MPa	ASTM D 790
Izod Impact notched, 1/8 in	128	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	80	°C	ASTM D 648
DTUL @ 264 psi	45	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	890	kg/m ³	ASTM D 792

Characteristics

Features

Copolymer

Regional Availability

North America

Applications

Medical