

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>24</b>	MPa	ASTM D 638
Elongation at Break	<b>425</b>	%	ASTM D 638
Flexural Modulus	<b>770</b>	MPa	ASTM D 790
Flexural Strength	<b>22</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>108</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>70</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>44</b>	°C	ASTM D 648

### Characteristics

#### Processing

Injection Molding

#### Regional Availability

North America

#### Special Characteristics

High impact or impact modified