

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	18	MPa	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	700	MPa	ASTM D 790
Flexural Strength	20	MPa	ASTM D 790
Izod Impact notched, 1/8 in	432	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	68	°C	ASTM D 648
DTUL @ 264 psi	44	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	915	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

North America

Features

Copolymer