

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Yield | 25 | MPa | ASTM D 638 |
| Flexural Modulus | 953 | MPa | ASTM D 790 |
| Flexural Strength | 30 | MPa | ASTM D 790 |
| Rockwell Hardness | R69 | - | ASTM D 785 |
| Izod Impact notched, 1/8 in | 419 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|--------------------|-------|------|---------------|
| ASTM Data | | | |
| DTUL @ 66 psi | 84 | °C | ASTM D 648 |
| DTUL @ 264 psi | 51 | °C | ASTM D 648 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 890 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Injection Molding

Regional Availability

North America

Features

Copolymer