

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	21	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 638
Flexural Modulus	1100	MPa	ASTM D 790
Izod Impact notched, 1/8 in	220	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	90	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Features

Copolymer, Impact Copolymer

Regional Availability

North America