

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	11.4	MPa	ASTM D 638
Elongation at Break	776	%	ASTM D 638
Flexural Modulus	415	MPa	ASTM D 790
Flexural Strength	10.8	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	39	°C	ASTM D 648
DTUL @ 264 psi	55	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	890	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Regional Availability

North America