

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	20.7	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	999.7	MPa	ASTM D 790
Rockwell Hardness	R80	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	24.4	°C	ASTM D 648
DTUL @ 264 psi	10	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Film Extrusion, Profile Extrusion, Coating

#### Regional Availability

North America

#### Special Characteristics

High impact or impact modified