

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	27	MPa	ASTM D 638
Elongation at Break	380	%	ASTM D 638
Flexural Modulus	1019	MPa	ASTM D 790
Flexural Strength	32	MPa	ASTM D 790
Rockwell Hardness	R73	-	ASTM D 785
Izod Impact notched, 1/8 in	137	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	96	°C	ASTM D 648
DTUL @ 264 psi	49	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Features

Copolymer

Regional Availability

North America