

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Flexural Modulus	1340	MPa	ASTM D 790
Flexural Strength	32	MPa	ASTM D 790
Rockwell Hardness	R75	-	ASTM D 785
Izod Impact notched, 1/8 in	716	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	88	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Blow Molding

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Regional Availability

North America