

Polypropylene PP 1329

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26	MPa	ASTM D 638
Elongation at Yield	300	%	ASTM D 638
Flexural Modulus	930	MPa	ASTM D 790
Izod Impact notched, 1/8 in	76.9	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	32	°C	ASTM D 648
DTUL @ 264 psi	13	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Applications

Automotive