

Polypropylene PP 1500-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	20	MPa	ASTM D 638
Elongation at Yield	24	%	ASTM D 638
Flexural Modulus	850	MPa	ASTM D 790
Rockwell Hardness	R70	-	ASTM D 785
Izod Impact notched, 1/8 in	513	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	75	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Features

Copolymer, Impact Copolymer