

Polypropylene PP 1500X-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	21	MPa	ASTM D 638
Flexural Modulus	1000	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	85	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

North America

Features

Copolymer, Impact Copolymer