

## Polypropylene PP 1632-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Rockwell Hardness	R85	-	ASTM D 785
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	95	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding, Blow Molding

#### Features

Copolymer, Random Copolymer

#### Certifications

Food contact, Food approval FDA 21 CFR

#### Regional Availability

North America