

Polypropylene PP 1930-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	1200	MPa	ASTM D 790
Thermal properties			
ASTM Data			
DTUL @ 66 psi	219	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

North America