

Polypropylene PP 3515

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26.9	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	85	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

North America

Certifications

Food contact, Food approval FDA 21 CFR