

POPELEN EH-314

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.7	g/10min	ASTM D 1238
Temperature	230	°C	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	12.8	MPa	ASTM D 638
Flexural Modulus	540	MPa	ASTM D 790
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	638	J/m	ASTM D 256
Temperature	-30	°C	-

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

High impact or impact modified

Features

Soft Feel, Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific