

POPELEN G-152

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.009	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	78.5	MPa	ASTM D 638
Flexural Modulus	4709	MPa	ASTM D 790
Rockwell Hardness	R 110	-	ASTM D 785
Izod Impact notched, 1/8 in	98.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	160	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Features

Copolymer

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific