

POPELEN SRX-373M

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	40	g/10min	ASTM D 1238
Temperature	230	°C	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	19.6	MPa	ASTM D 638
Flexural Modulus	1962	MPa	ASTM D 790
Flexural Strength	27.5	MPa	ASTM D 790
Izod Impact notched, 1/8 in	490	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	78.5	J/m	ASTM D 256
Temperature	-30	°C	-
Thermal properties			
ASTM Data			
DTUL @ 66 psi	130	°C	ASTM D 648
Other properties			
Density	990	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

High impact or impact modified

Features

Copolymer

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific