

**POPELEN V-235N**

PP

Lotte Chemical Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>6</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>32.4</b>	MPa	ASTM D 638
Flexural Modulus	<b>2943</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 90</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>29.4</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
DTUL @ 66 psi	<b>135</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1300</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Features**

Copolymer

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific