

PP 1500M (X30G)

PP

Nizhnekamskneftekhim OAO

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	34	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1400	MPa	ASTM D 790

Characteristics**Delivery form**

Pellets

Chemical Resistance

Oxidation Resistance

Features

Thermal Stability, Homopolymer

Regional Availability

Europe, Asia Pacific