

**PP 1500P (V30G)**

PP

Nizhnekamskneftekhim OAO

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>17.5</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Flexural Modulus	<b>1400</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>24</b>	J/m	ASTM D 256

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Pellets

**Chemical Resistance**

Oxidation Resistance

**Features**

Thermal Stability, Homopolymer

**Regional Availability**

Europe, Asia Pacific