

PP 1528J (T38FA)

PP

Nizhnekamskneftekhim OAO

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.05	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	34	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1450	MPa	ASTM D 790

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Features

Thermal Stability, Homopolymer

Delivery form

Pellets

Chemical Resistance

Oxidation Resistance

Special Characteristics

Anti-static

Regional Availability

Europe, Asia Pacific