

**PP colored 43000**

PP

LH-Plastics GmbH

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[5]</sup></b>			
Melt flow index, MFI	<b>3</b>	g/10min	-
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[5]</sup></b>			
Melting temperature, 10°C/min	<b>160</b>	°C	-

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Moisture Content	<b>0.2</b>	%	-
<b>Other Standards<sup>[5]</sup></b>			
Density	<b>910</b>	kg/m <sup>3</sup>	-

S: These properties are reported by the producer according standards that are different to our defaults.

**Characteristics****Delivery form**

Pellets

**Regional Availability**

Europe

**Certifications**

Recycled Resin Content