

PP H250 GP

PP

SIBUR Holding OJSC

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1500	MPa	ISO 178

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific