

PP regranulate

PP

Qualchem Zrt.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	27	MPa	ISO 527
Yield strain	11	%	ISO 527
Stress at break	22	MPa	ISO 527
Strain at break	>50	%	ISO 527

Characteristics**Processing**

Injection Molding

Certifications

Recycled Resin Content

Delivery form

Brown

Regional Availability

Europe