

PRIMATOP® PP 350-10 RC

PP

Amco Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	27.9	MPa	ASTM D 638
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	82.2	°C	ASTM D 648
Other properties			
Other Standards^[S]			
Density	900	kg/m ³	ASTM D 1505

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Injection Molding

Additives

Release agent

Special Characteristics

Transparent

Features

Copolymer, Random Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America